

Technical Data Sheet (ASTM)

**ABS(Acrylonitrile Butadiene Styrene)
ER-875A**

Features ESCR, Injection molding use
Applications Injection loded products: Regrigerator door cap etc(HCFC-141B foaming agen
Bidet

Physical	Test Method	Value
Density	ASTM D792	1.04 g/cm ³
Melt Flow Index (220°C, 10kg)	ASTM D1238	17 g/10min
Melt Flow Index (200°C, 21.6kg)	ASTM D1238	25 g/10min
Mold Shirinkage	ASTM D955	0.5 ~ 0.8 %
Water absorption	ASTM D570	- %
Mechanical	Test Method	Value
Tensile Strength	ASTM D638	410 kgf/cm ² (5,8286) (psi)
Elongation	ASTM D638	25 %
Flexural Strength	ASTM D790	530 kgf/cm ² (7,534) (psi)
Flexural Modulus	ASTM D790	18,000 kgf/cm ² (255,882) (psi)
Izod Impact Strength(3.2mm, 23°C)	ASTM D256	45 kgf-cm/cm (8.3) (ft-lb/in)
Izod Impact Strength(6.4mm, 23°C)	ASTM D256	30 kgf-cm/cm (5.5) (ft-lb/in)
Rockwell Hardness(R scale)	ASTM D785	99
Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	84 °C (183) (°F)
Vicat Softening Temperature(5kg, 50°C/h)	ASTM D1525	94 °C (201) (°F)
Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.