

FEATURES

- Low residual styrene monomer content
- Moderate heat resistance
- Good balance of strength and ease of processing
- USP Class VI certified
- UL Classification 94 HB (www.UL.com file E57787)

APPLICATIONS

- Foam extrusion
- Thermoformed drinkware
- Food service and food packaging containers
- Point of purchase displays
- Applications that require high clarity and no taste or odor transfer

| Property, Test Condition | Standard | Unit | Values |
|--------------------------------------------------------------|-------------|-----------------------|---------|
| Rheological Properties | | | |
| Melt Flow Rate, 200 °C/5 kg | ASTM D 1238 | g/10 min | 3.4 |
| Mechanical Properties | | | |
| Izod Notched Impact Strength, 23 °C (73 °F) | ASTM D 256 | ft-lb/in | 0.4 |
| Tensile Stress at Yield, 23 °C | ASTM D 638 | psi | 6400 |
| Tensile Modulus | ASTM D 638 | psi x 10 ³ | 460 |
| Elongation, Failure | ASTM D 638 | % | 2 |
| Flexural Strength, 23 °C | ASTM D 790 | | 12000 |
| Flexural Modulus, 23 °C | ASTM D 790 | psi x 10 ³ | 480 |
| Hardness, Rockwell | ASTM D 785 | M scale | 75 |
| Thermal Properties | | | |
| Vicat Softening Temperature, B/1 (120 °C/h, 10N) | ASTM D 1525 | °F | 205 |
| Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa) | - | °F | 195 |
| Coefficient of Linear Thermal Expansion | ASTM D 696 | 10 ⁻⁴ /°F | 0.4 |
| Electrical Properties | | | |
| Dielectric Constant at 106 CPS (1000000 Hz, 0,0394 in) | ASTM D 150 | - | 2.5 |
| Dielectric Strength, 1/8" | ASTM D 149 | kV/in | 500 |
| Optical Properties | | | |
| Refractive Index, Sodium D Line | ASTM D 542 | - | 1.59 |
| Light Transmission at 550 nm | ASTM D 1003 | % | 88 - 90 |

Styrolution PS 2600/2601

General Purpose Polystyrene (GPPS)

TECHNICAL DATASHEET

| Property, Test Condition | Standard | Unit | Values |
|-------------------------------------------|------------|--------------------|-------------|
| Optical Density, 400–700 nm avg. | - | - | 0.046 |
| Other Properties | | | |
| Density (ASTM) | ASTM D 792 | g/cm ³ | 1.04 |
| Bulk Density (without external lubricant) | - | lb/ft ³ | 37 - 40 |
| Bulk Density (with external lubricant) | - | lb/ft ³ | 42 - 45 |
| Processing | | | |
| Linear Mold Shrinkage | ASTM D 955 | in/in | 0.004-0.007 |
| Melt Temperature Range | - | °F | 375 - 525 |
| Mold Temperature Range | - | °F | 100 - 180 |

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.

Please consult our local sales or technical representatives for details.

SUPPLY FORM

Styrolution PS 2600 can be supplied in two versions, with (grade name ending in 1) or without an external lubricant (grade name ending in 0) for improving pneumatic conveying. Styrolution PS resins are available in bulk railcar and bulk truckload quantities.

PRODUCT SAFETY

Styrolution PS resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of Styrolution PS resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact Styrolution Technical Service for further information on recycling and disposal of Styrolution resins.

DISCLAIMER

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.