

Technical Data Sheet

**HIPS(High Impact Poly Styrene)
MIB 237**

Features

Demoldability

Applications

Yogurt beverage bottles, Disposable cups

Physical	Test Method	Value
Density	ASTM D792	1.03 g/cm ³
Melt Flow Index (200°C, 5kg)	ASTM D1238	9.5 g/10min
Mold Shrinkage	ASTM D955	0.3 ~ 0.6 %
Water absorption	ASTM D570	0.03 %

Mechanical	Test Method	Value
Tensile Strength	ASTM D638	250 kg/cm ² (3,550) (psi)
Elongation	ASTM D638	40 %
Flexural Strength	ASTM D790	380 kg/cm ² (5,396) (psi)
Flexural Modulus	ASTM D790	19,000 kg/cm ² (269,800) (psi)
Izod Impact Strength(3.2mm)	ASTM D256	8.0 kgcm/cm (1.48) (ft-lb/in)
Rockwell Hardness(L scale)	ASTM D785	70

Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	75 °C (167) (°F)
Vicat Softening Temperature(1kg, 50°C/h)	ASTM D1525	93 °C (199) (°F)

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.

Technical Data Sheet

HIPS(High Impact Poly Styrene) MIB 237

Processing guide

Injection Guide	Unit	Value
Nozzle	°C	190~220
Front	°C	190~210
Middle	°C	180~200
Rear	°C	170~190
Hopper Throat	°C	45
Mold	°C	40~60

Drying	Unit	Value
Temperature	°C	60~70
Time	hr	1~3

Notes

These are only mentioned as general guidelines.