

## KUMHO PETROCHEMICAL

KUMHO BLDG 57, 15TH &amp; 16TH FL, 57 SHINMMUNRO, 1-KA, CHONGNO-KU, SEOUL 110-061 KR

## ABS-775T

Acrylonitrile Butadiene Styrene (ABS), furnished as pellets

Color	Min Thk (mm)	Flame Class	HWM	HAI	RTI Elec	RTI Imp	RTI Str
ALL	HB	1.5	3	0	60	60	60
	HB	3.0	3	0	60	60	60

Comparative Tracking Index (CTI): 0

High-Voltage Arc Tracking Rate (HVTR): 2

Dielectric Strength (kV/mm): -

Dimensional Stability (%): -

High Volt, Low Current Arc Resis (D495): 6

Volume Resistivity (10<sup>x</sup> ohm-cm): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1993-06-09

Last Revised: 2006-08-09

Underwriters Laboratories Inc®



## IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
IEC Flammability	IEC 60695-11-10	Class (color)	HB	1.5 (ALL)
			HB	3.0 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m <sup>2</sup>	-	-
ISO Izod Impact	ISO 180	kJ/m <sup>2</sup>	-	-
ISO Charpy Impact	ISO 179-2	kJ/m <sup>2</sup>	-	-

Underwriters Laboratories Inc®