

## SOL-C6450SL

### Solution Styrene Butadiene Rubber (SSBR)

#### Product Introduction

- Kumho SOL-C6450SL is solution styrene butadiene rubber manufactured by anionic solution polymerization using alkyllithium initiator in organic solvent.
- It is oil extended SSBR.
- Its processibility, viscoelastic property and cold flexibility are superior to emulsion SBR.
- Kumho SSBR can be properly controlled in styrene %, Vinyl % and molecular weight and provides a wide range of styrene, vinyl and mooney level to optimize performance in variety of tire and industrial application, as it uses innovative coupling and funtionalizing technology.

#### Product Properties

Property	Typical value	Test Method
Styrene (%)	35	NMR MRTHOD
Vinyl (% , in BD)	40	NMR METHOD
ML1+4	53	ASTM D 1646
Tg (°C)	-36	ISO 11357-2
Oil content (%)	27.3	ASTM D 5774

#### Characteristics and Applications

- Typical application is for tire tread by mixing with NR, BR and any other rubber.
- Compatible with silica, as well as carbon black, so many advantage characteristics are observed in carbon black compound for tire tread such as increasing bound rubber, good filler dispersion, higher wet traction, lower rolling resistance, lower heat build-up and lower mill shrinkage.

#### Manufacturer location

- Yeosu plant in Korea

#### Product safety

- Relevant safety data and references can be found in the safety data sheet.

#### Shelf life/Conditions

- 2 years from the production date at temperatures not exceeding 35°C, keeping away from direct sunlight, humidity

#### Packaging

- Bale weitht : 35kg
- '- Pallet weight : 1,050kg (30 bales) or 1,260kg (36bales)

Head Office (Sales)  
East Wing 10-14th Floor, Signature Towers Seoul,  
100 Cheonggyecheon-ro, Jung-gu, Seoul, Korea  
TEL +82-2-6961-1114 Fax +82-2-6961-1459  
[www.kkpc.com](http://www.kkpc.com)

Research Center (Technical Service)  
1557, Yuseongdae-ro, Yuseong-gu, Daejeon, Korea  
TEL +82-42-865-8600 Fax +82-42-862-5651

Yeosu Plant (Quality Assurance)  
331, Sandanjangang-ro, Yeosu, jennam, Korea  
TEL +82-61-688-7210 Fax +82-61-688-7219